

TECHNICAL DATA SHEET**SEAMASTER 6300 ROOFING PAINT**

Description	6300 Roofing Paint is a one pack chlorinated rubber modified finish designed for roof coating. It has Impervious to water and many chemical, fungus resistance. It dries at low temperatures, easy to touch up and overcoat after extended periods, flexibility and elongation properties enable roof coating to bridge hairline cracks.
Surface Preparation	Must be applied to a suitably primed surface. The surface of the primer must be clean, dry and free from grease
Physical Properties	
Vehicle Type	Chlorinated polymer
Pigmentation	Selected chemical and weather resistance types
Mixing Ratio	Single pack
Density (kg / litre)	1.10 – 1.35
Volume Solid	34 ~ 37% (depends on colour)
Drying Time at (27 ± 2°C & RH 80 ± 5%)	Surface Dry ≤ 10 mins Touch Dry ≤ 20 mins Hard Dry ≤ 3 hrs
Recoating Interval	4 hrs (minimum), indefinite (maximum)
Dry Film Thickness	40 microns
Wet Film Thickness	118 microns
Theoretical coverage	9.3 m ² / litre
Colour	Selected range
Finish	Gloss
Storage Conditions	Air tight, store in dry and cool condition
Pot Life	Not applicable
Cleaner	S4002 Thinner
Shelf Life	Not applicable
Application Temperature	5° to 40°C
Packing	1 litre, 5 litres
Application method	By brush or roller
Thinning	Not recommended. If necessary use S4002 Thinner
Safety Precautions	
Health and safety	Please refer to P.P.A. 3/1 and Safety Data Sheet
Fire Risk	Inflammable flash point (abel closed cup) 32° C
Toxicity	Solvent toxic in confined spaces. Use adequate ventilation.



TECHNICAL DATA SHEET

SEAMASTER 6300 ROOFING PAINT

Product Liability

The Seller warrants the product to be free from manufacturing defects in material and workmanship. The Seller's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited at the Seller's option, to either replacement of products not conforming to this warranty or credit to the Buyer's account in the invoiced amount of the non-conforming products.

The Seller makes no other warranties concerning this product. No other warranties, either express or implied, or satisfactory, and as warranties or merchantability or fitness for a particular purpose, shall apply. In no event shall the Seller be liable for consequential or incidental damages. Any recommendations or suggestion relating to the use of the products made by the Seller, whether in its technical limitation, or in response to specific inquiry, or otherwise, is based on data believed to be reliable, however, the products and information are intended for Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that the Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

